



FJ00952

High Density Polyethylene for Blown film

Product Description

FJ00952 is TNPP additive free, high molecular weight high density polyethylene copolymer grade specifically designed for blown film applications. Its high molecular weight, broad molecular weight distribution and high density combine successfully to give excellent extrudability with high film strength and rigidity.

Typical Applications

FJ00952 resin is recommended for blown film extrusion. This product is suggested for the manufacture of high strength grocery sacks, shopping bags and high quality thin films for multi wall sack liners and replacement for thin paper products. Films of this product can be readily treated and printed to give high quality graphics.

Typical data

Properties	Unit	Value ⁽¹⁾	Test Method
Melt Flow Rate @ 190°C & 2.16 kg load	g/10 min.	0.05	ASTM D 1238
@ 190°C & 21.6 kg load		9	
Density @ 23°C	kg/m ³	952	ASTM D 1505
Mechanical Properties ⁽²⁾			
Tensile Strength @ break, MD TD	MPa	60 56	ASTM D 882
Tensile Elongation @ break, MD TD	%	400 550	ASTM D 882
Tensile Strength @ yield, MD TD	MPa	33 31	ASTM D 882
1% Secant Modulus, MD TD	MPa	1250 1500	ASTM D 882
Dart Impact Strength	g	180	ASTM D 1709
Elmendorf Tear Strength, MD TD	g	12 60	ASTM D 1922
Thermal Properties			
Vicat Softening Point	°C	125	ASTM D 1525

(1) Typical values; not to be construed as specification limits.

(2) Properties are based on 15 µm film produced at 4 BUR using 100% FJ00952.

Processing Conditions

Melt Temperature: 200 - 235°C

Frost Line Height: 6 - 8 times die Ø

BUR: 3 - 5

Food Regulation

FJ00952 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia
Tel: 966 1 2258000
Fax: 966 1 2259000

Technical Marketing
Tel: 966 1 2659166
Fax: 966 1 2653544
Toll-free 800 1245577

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.